

TEST REPORT

APPLICANT: PT. INDAH KIAT PULP AND PAPER TBK
JL RAYA SERANG KM. 76 KRAGILAN,
SERANG-BANTEN, 42184

ATTN: FINI FITRIANI

DATE: JANUARY 17, 2024

THE SUBMITTED SAMPLE SAID TO BE:

SAMPLE DESCRIPTION : FOOPAK BIO NATURA
PRODUCT COLORS : PAPER WHITE
COUNTRY OF ORIGIN : INDONESIA
MANUFACTURER NAME : PT INDAH KIAT PULP AND PAPER TBK
TESTING STAGE : PRODUCTION SAMPLE

TESTS CONDUCTED:

AS REQUESTED BY THE APPLICANT, FOR DETAILS REFER TO ATTACHED PAGES.

CONCLUSION:

<u>TESTED SAMPLE</u>	<u>STANDARD</u>	<u>RESULT</u>
SUBMITTED SAMPLE	COUNCIL OF EUROPE RESOLUTION CM/RES (2020) 9 AND EDQM TECHNICAL GUIDE ON PAPER AND BOARD USED IN FOOD CONTACT MATERIALS AND ARTICLES, 2021, 1 ST EDITION ON OVERALL MIGRATION	SEE TEST CONDUCTED

Remark:

1. Overall Migration Test was subcontracted to Intertek China.
2. This report was extracted from report no. JKTH23003093REV1 as per client request.

PREPARED AND CHECKED BY:
FOR INTERTEK INDONESIA



TAUFIQ URAKHMAN
HARDLINE LAB MANAGER

RT/AD/IS

The report shall not be reproduced wholly or in parts without written approval of the laboratory.
Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Terms and Conditions.
For the complete term and condition, please visit: <http://www.intertek.com/terms>



TESTS CONDUCTED:

- (1) Overall Migration Test for Paper and Board

With reference to Commission Regulation (EU) No. 10/2011 and its amendments .

Test Results :

Test component (1)

<u>Test Simulant</u>	<u>Test condition</u>	<u>Result</u> (mg/dm ²)	<u>Reporting Limit</u> (mg/dm ²)	<u>Limit</u> (mg/dm ²)
10% (v/v) Ethanol	1 hour at 5°C	6	3	10
	1 hour at 20°C	8	3	10
20% (v/v) Ethanol	1 hour at 5°C	9	3	10
50% (v/v) Ethanol	1 hour at 5°C	4	3	10
	1 hour at 20°C	4	3	10
95% (v/v) Ethanol	1 hour at 5°C	5	3	10
	1 hour at 20°C	6	3	10
	1 hour at 40°C	6	3	10
MPPO	1 hour at 220°C	5	3	10

Note : As per client's request, the above condition and food simulant were used for the test.

The report shall not be reproduced wholly or in parts without written approval of the laboratory.
Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Terms and Conditions.
For the complete term and condition, please visit: <http://www.intertek.com/terms>



Ratio of food contact surface area to volume of component (1) used to establish the compliance of material or article = 1 dm²
: 100 mL.

The limit quoted is for reference only.

Tested component(s) : (1) White paper board.

Date Sample Received : September 20, 2023
Testing Period : September 20, 2023 to November 15, 2023


END OF REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

The report shall not be reproduced wholly or in parts without written approval of the laboratory.
Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Terms and Conditions.
For the complete term and condition, please visit: <http://www.intertek.com/terms>



PRODUCT PHOTO



EXH 1

The report shall not be reproduced wholly or in parts without written approval of the laboratory.
Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Terms and Conditions.
For the complete term and condition, please visit: <http://www.intertek.com/terms>

